

Data sheet

OpDAT fiber OS2

Technical Data

General Data

Fiber class	OS2 (ITU-T G.657.A2)
Fiber construction	9/125 µm

Transmission characteristics

Chromatic dispersion coefficient - At 1550 nm (max.)	<= 18 ps/km * nm
Polarisation mode dispersion (PMD) coefficient, cabled (max.)	<= 0.2 ps/vkm

Geometric characteristics

Fiber core diameter	Ø 9 µm
Primary coating diameter	242 µm
Fiber cladding non-circularity	max. 0.7 %
Core (MDF)-cladding concentricity error	max. 0.5 µm
Primary coating concentricity error	max. 5 %
Primary coating-cladding concentricity error	max. 12 µm

Optical characteristics

Attenuation of the fiber in the cable at 1310 nm	max. 0.4 dB/km
Attenuation of the fiber in the cable at 1383 nm	max. 0.4 dB/km
Attenuation of the fiber in the cable at 1550 nm	max. 0.25 dB/km
Attenuation of the fiber in the cable at 1625 nm	max. 0.25 dB/km
10 turns on a mandrel R= 15 mm, 1550 nm	max. 0.03 dB
1 turn on a mandrel R= 10 mm, 1550 nm	max. 0.1 dB
1 turn on a mandrel R= 7.5 mm, 1550 nm	max. 0.5 dB
Group refractive index at 1310 nm	1.467
Group refractive index at 1550 nm and 1625 nm	1.468

Application note

This product is a standard product of METZ CONNECT. METZ CONNECT is not aware of the specific intended use of the goods by the Customer or any customers of the Customer. The Customer guarantees that it has fully and sufficiently tested the use of the goods and any product modifications, product changes or product enhancements with regard to the specific intended use in accordance with the state of the art or in any other way. At METZ CONNECT's request, the Customer shall submit and make available meaningful evidence (e.g. test and laboratory protocols, certifications, etc.).